

Abstract of the Disclosure

An epitaxial structure of GaN based compound semiconductor comprises a substrate; a single crystal of boron phosphide buffer layer on the substrate; a first buffer layer composed of group III nitride at a temperature from 200 to
5 800 degree C formed on the boron phosphide buffer layer; and a second buffer layer composed of group III nitride at a temperature from 800 degree formed on the first buffer layer.